

# FILLER GUM




## Product descriptions

REF No.	MODEL No.	DESCRIPTION
29962	FG-02	2kg 3.0mm × 500mm × about 1m
29965	FG-05	5kg 3.0mm × 500mm × about 2.5m

## Properties

- Use for large injuries that cannot be filled with stems.
- Specially compounded to have the same strength as tire rubber after vulcanization.
- Use hot curing only.
- Apply 140°C heat for 4 minutes or more for each millimeter of thickness.  
(Warm up times for equipment require a separate 20 to 30 minutes)
- Shelf life: 1.5 years at 20°C when direct sunlight and humidity are avoided



Coat THERMO LIQUID onto the skived and buffer area of the tire inside and out. Build up the skive with FILLER GUM as illustrated in the left column. Allow slight overfilling at center of damage.